


2014 TXDOT STANDARD SPECIFICATIONS

<u>ITEM NO.</u>	<u>TITLE</u>	<u>SECTION NO.</u>	<u>CITY OF TYLER EXCEPTION</u>
164	SEEDING FOR EROSION CONTROL	2.1 - TABLE 1	DISREGARD TABLE 1 - PERMANENT RURAL SEED MIX. USE TABLE 2 - PERMANENT URBAN SEED MIX, OR AS SPECIFIED BY ENGINEER.
247	FLEXIBLE BASE	2.1 - TABLE 1	DISREGARD TEX-117-E FOR MINIMUM COMPRESSIVE STRENGTH. USE CBR AND MAXIMUM PI = 9.
247	FLEXIBLE BASE	4.3.2	COMPACTION TO BE DETERMINED USING ASTM D698 OR ASTM D1557 INSTEAD OF TEX-115-E OR TEX-103-E.
260	LIME TREATMENT (ROAD-MIXED)	4.5	COMPACTION SHALL BE IN ACCORDANCE WITH CITY OF TYLER STANDARD DETAIL "TESTING REQUIREMENTS FOR PAVING".
265	FLY ASH OR LIME-FLY ASH TREATMENT (ROAD-MIXED)	4.4	COMPACTION SHALL BE IN ACCORDANCE WITH CITY OF TYLER STANDARD DETAIL "TESTING REQUIREMENTS FOR PAVING".
275	CONCRETE TREATMENT (ROAD-MIXED)	4.5	COMPACTION SHALL BE IN ACCORDANCE WITH CITY OF TYLER STANDARD DETAIL "TESTING REQUIREMENTS FOR PAVING".
275	CONCRETE TREATMENT (ROAD-MIXED)	4.7	MICROCRACKING IS NOT ALLOWED UNLESS SPECIFIED BY THE ENGINEER.
340	DENSE-GRADED HOT-MIX ASPHALT (SMALL QUANTITY)	2.7.2	USE OF RECYCLED ASPHALT SHINGLES (RAS) IS NOT ALLOWED.
340	DENSE-GRADED HOT-MIX ASPHALT (SMALL QUANTITY)	2.1.1	COARSE AGGREGATE TO BE CRUSHED SO THAT A MINIMUM OF 50% OF PARTICLES RETAINED ON #4 SIEVE HAVE MORE THAN ONE CRUSHED FACE WHEN TESTED IN ACCORDANCE WITH TEX-460-A.
348	THIN BONDED FRICTION COURSES	2.7.2	USE OF RECYCLED ASPHALT SHINGLES (RAS) IS NOT ALLOWED.
421	HYDRAULIC CEMENT CONCRETE	4.2.1 - TABLE 8	DESIGN STRENGTH FOR CLASS A AND CLASS C CONCRETE SHALL BE ATTAINED IN 28 DAYS, NOT 56 DAYS.
465	JUNCTION BOXES, MANHOLES, AND INLETS	ALL	USE CITY OF TYLER STANDARD SPECIFICATIONS AND/OR DETAILS IN LIEU OF THIS ITEM.



CITY OF TYLER
STANDARD DETAIL

**CITY OF TYLER EXCEPTIONS
TO TXDOT STANDARD SPECIFICATIONS**

REVISION DATE:
MAY 14, 2021